



1215 ELASTOMERIC, TEXTURED BRUSH GRADE, CAULK & SEALANT

DESCRIPTION

Anvil #1215 Elastomeric, Textured Brush Grade Caulk & Sealant is a heavy bodied, flexible, elastomeric patching material for filling and patching cracks joints and seams on; masonry, stucco, concrete block and metal prior to applying finish. **Anvil #1215 Elastomeric, Textured, Brush Grade Caulk & Sealant** provides excellent adhesion, long life, and is resistant to failure by expansion, contraction, or other joint movement. Fast drying and may be painted with latex or oil base paints. For use on interior or exterior surfaces.

SURFACE PREPARATION

Surface must be free of dirt, oil, grease, efflorescence, chalk, mildew, and loose material. Any residual chalk left after pressure washing should be sealed with **Anvil #230 or #231 Chalky surface conditioner**. New Galvanized metal should be treated to remove mill oils. Ferrous metal should be free from rust and primed with **Anvil #1606 Rust Inhibitive Primer Sealer**.

APPLICATION

Apply with brush or roller. Build up area by layering application. Allow to dry thoroughly before applying a new layer. Fiberglass mesh may be used between layers to bridge seam or crack.

LIMITATION OF LIABILITY

This product is manufactured to rigid control specifications. It is impossible to control the use and application. Therefore, the manufacturers sole liability is limited to replacing quantities of product proven to be defective. The manufacturer disclaims any liability for the cost of labor to repaint or any other use of the product.

Page 1 Of 1

TECHNICAL DATA

PRODUCT NUMBER: 1215 Elastomeric Textured Brush Grade Caulk & Sealant

RESIN: Acrylic Latex

COLOR: White

GLOSS: Flat

SOLID CONTENT:
BY WEIGHT: 59.1%
BY VOLUME: 51.4%

RECOMMENDED COVERAGE:
10 to 20 Sq. Ft./Gal.

% PIGMENT BY WEIGHT: 28.1%

% VEHICLE BY WEIGHT: 71.9%

VISCOSITY: Mastic-like

WEIGHT PER GALLON: 9.9 lbs

FLASH POINT: N/A

DRYING TIME @ 70° F 50% R.H:
Touch - 1 hour
Paint over - 2 to 4 hours
Full cure - 1/8" thick single coat - 72 hours
Do not apply when rain, cold or nightfall is imminent. do not apply below 50° F. Drying and cure time are influenced by ambient temperature and relative humidity.

THINNER/CLEANUP: Water

TINTING: Not Recommended

VOC: 90.33 grams/liter
AVAILABLE IN 1 & 5 GALLON PAILS

Revised 1-09 Supersedes all prior publications GRO